


EXTERNAL SCREEN CLASSIC ULTRAVISION



INTELLIGENT FABRICS FOR SOLAR PROTECTION



www.mermet.co.uk 01989 750910 info@mermet.co.uk

ULTRAVISION

OPEN TEXTILE ENVELOPE FOR EXTERNAL AND INTERNAL APPLICATION

37 %

OF VISIBLE LIGHT TRANSMITTANCE

TOTAL TRANSPARENCY


- VERY OPEN-WEAVE FABRIC (OF 25%) for maximum use of NATURAL LIGHT, comfort classification 3 (good effect) according to EN 14501 standard
- Helps reduce energy consumption in buildings with less artificial light is required. Artificial light is a key source of energy consumption in commercial buildings
- THERMAL COMFORT: up to 86% OF SOLAR RADIATION REFLECTED by external blinds (gtot = 0,14 / glazing g = 0,32 and U = 1,1)
- WEATHER-RESISTANT and UV fading resistant
- EXCELLENT DURABILITY: mechanical strength test of 10.000 cycles (class 3 NF EN 13561)
- Health & Safety: conforms to standard requirements for buildings open to the public

TECHNICAL DATA

ULTRAVISION						
Composition	42% Fibreglass - 58% PVC					
Fire, smoke classification and other official test reports	M1 (F) - NFP 92 503 BS (GB) - 476 Pt 6 & 7 Class 0					
Health, safety	Greenguard®: Guarantee of indoor air quality (VOC)					
Openness factor	25%					
UV screen	Up to 76%					
Width	250 cm					
Weight/m²	365 g ± 5% - ISO 2286 - 2					
Thickness	0,65 mm ± 5% - ISO 2286 - 3					
Colour Fasteness to light (scale of 8)	7/8 - ISO 105 B02 (white not graded)					
Mechanical resistance	Breaking	Tear	Folding			
Warp	> 160 daN/5 cm	≥ 10 daN	≥ 120 daN/5 cm			
Weft	> 100 daN/5 cm	≥ 10 daN	≥ 70 daN/5 cm			
	ISO 1421	EN 1875-3	ISO 1421			
Elongation (warp and weft)	< 5% - ISO 1421					
Packaging	Rolls of 52 lm					
Making up	Advice note on request					

This product's technical data are in conformity with this brochure as of the date of publication. MERMET SAS reserves the right to change the technical data; only those provided on the company's website www.sunscreen-mermet.com shall be deemed to be authentic. Where applicable, MERMET SAS also reserves the right to withdraw this product from sale should any of the technical properties or characteristics set out above prove to be inadequate or rendered impossible as a result of a change in regulations or in knowledge or understanding.

ULTRAVISION



0201

THERMAL AND OPTICAL FACTORS the European standard EN 14501


ULTRAVISION	Thermal factors					Optical factors
OF 25%	Fabric		Fabric + Glazing / gtot external blind		T.	
Colours	Ts	Rs	As	C : gv = 0,59	D : gv = 0,32	Tv
0202 White	38	52	10	0,27 2	0,15 2	37
0707 Pearl	35	30	35	0,24 2	0,14 🕄	35
0201 White Grey	34	37	29	0,24 2	0,14 🕄	33
0701 Pearl Grey	33	26	41	0,22 2	0,14 📵	32

gv = 0,59: Solar factor of standard glazing (C), low-emission 4/16/4 double glazing filled with Argon (U value thermal transmittance = 1,2 W/m²K). gv = 0,32: Solar factor of standard glazing (D), reflecting low-emission 4/16/4 double glazing filled with Argon (U value thermal transmittance = 1,1 W/m²K).


Classification according to EN 14501 standard: 0 very little effect 0 little effect 2 moderate effect 3 good effect 4 very good effect

Samples tested according to EN 14500 standard defining the measurements and calculation methods as specified in the standard EN 13363-2 "Solar protection devices combined with glazing calculation of solar and light transmittance - part 2: EN 13363-2 detailed method" and EN 410 "Glass in building - Determination of luminous and solar characteristics of glazing".

ULTRAVISION



0201




















SERVICE

- Calculation of solar factor gtot (glazing + blind)
- Spectral values and thermal & optical factors available on request
- Specification sheet
- A4 samples and prototypes
- Training on fabrics functionality





MERMET U.K. Ryeford Hall, Ryeford, Ross-on-Wye HR9 7PU Phone 01989 - 750910 Fax 01989 750768 info@mermet.co.uk